

Product and Application

TruSTRENGTH 130 plate provides excellent properties in strength and toughness. This quenched and tempered product excels in downstream fabrication processes like bending, machining laser cutting, plasma cutting and welding. This product is used widely in construction and forestry equipment, mining, cranes, heavy-duty transport equipment, railcars and various applications requiring a high strength-to-weight ratio.

Available in thicknesses up to 0.500", widths up to 60" and lengths up to 288".

Mechanical Properties

Yield Strength (min.)	130 ksi (896 MPa)
Tensile Strength (min.)	140 ksi (965 MPa)
Elongation	12%
Reduction of Area	45%
Charpy V-Notch @ -40° F	38 ft-lbs (51.5 J) longitudinal, 30 ft-lbs (40.7 J) transverse
Charpy V-Notch @ -40° F (min.)	20 ft-lbs (27.1 J) transverse
Bend Radius	2.5T (longitudinal), 3T (transverse). Larger bend radius recommended for thicker plates.

Typical values unless otherwise noted.

Different Charpy Impact test temperatures may be specified, with mechanical tests conducted in accordance with ASTM A370, latest revision. Tensile and Charpy Impact tests conducted per heat/heat treat lot. Hardness also taken on each plate, but not reported.

Dimensional Tolerances

Flatness	Flatness tolerances meet 1/2 of ASTM A6, Table 14, latest revision. TruFLAT tolerance of 1/4 ASTM A6 for 0.300" and thinner.
Thickness	+/- 0.012" to nominal thickness
Length and Width	Length and width tolerances meet ASTM A6, latest revision

TRUFLAT™

Chemical Composition

	C	Mn	P	S	Si	Cu	Ni	Cr	Mo
Max	0.24	1.60	0.020	0.015	0.34	0.25	0.45	0.65	0.30
CEV (typical):			0.58	CEV = C + Mn/6 + (Cr+Mo+V)/5 + (Ni+Cu)/15					
CET (typical):			0.40	CET=C + (Mn+Mo)/10 + (Cr+Cu)/20 + Ni/40					
CEq (typical):			0.39	CEq= C + Si/25 + (Mn+Cu)/16 + Ni/40 + Cr/10 + Mo/15 + V/10					

Fabrication, Bending, Post-Delivery Heating and Welding

Bending	Free bending should be performed utilizing maximum allowable bend radius to prevent cracking. TruSTRENGTH 130 plates can be bent using a minimum radius of 2.5T in the longitudinal direction and a minimum of 3T in the transverse direction. Larger bend radius is recommended for thicker plates. Transverse radius is the bend line parallel to rolling direction.
Welding	TruSTRENGTH 130 plate can be welded by conventional processes such as SMAW, SAW and GMAW, provided that the weld procedures used are suitable for this grade and design of the welded structure, using low hydrogen conditions.

*These statements are general guidelines. CMC Impact Metals is not responsible for the results of any welding work performed.

Standard Delivery Conditions

Surface Finish	Shot blasting and rust preventative applications are available. Please inquire.
Test Reports	Supplied with shipment for each production lot in the shipment. Reports include product description, heat number, chemical analysis and Brinell hardness value.